



RDX-K



Chemical Properties	Minimum	Maximum
RDX in R310	98	99
Wax in R310	0.7	1.3
Graphite%	0.3	0.7
Bulk Density, Standard Vessel	0.90	-----
Moisture	-----	0.1%
Flow, 50g/sec	-----	30
% Passing USSS 20	95	100
% Passing USSS 50	20	50
% Passing USSS 100	0	10
% Passing USSS 200	0	5

Shipping Information

Quantity per box: 50 lb
Hazard Class: 1.1D, EX -2000100066

STORAGE

RDX® must be stored in a dry, ventilated magazine and away from explosives and flammable products, according to applicable legislation.

When kept in its original package and properly stored, the shelf life is five (5) years.

Petro-Explo, Inc.

7650 U.S. Hwy. 287, #100, Arlington, Texas 76001
Phone: 817-478-8888 800-588-8282 Fax: 817-478-8891
email: info@petroexplo.com